

Application No.: 10/053396

Case No.: 56313US009

AmendmentsAmendments to the Claims:


The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

1. (Original) A fluorochemical composition comprising a major amount of organic solvent and 0.05% by weight to 5% by weight of fluorochemical oligomer dispersed or dissolved in said organic solvent and said fluorochemical oligomer being represented by the general formula:




wherein X represents the residue of an initiator or hydrogen; M^f represents units derived from fluorinated monomers; M^h represents units derived from a non-fluorinated monomers; M^a represents units having a silyl group represented by the formula:



wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group; G is a monovalent organic group comprising the residue of a chain transfer agent; n represents a value of 1 to 100; m represents a value of 0 to 100;

r represents a value of 0 to 100; and $n+m+r$ is at least 2;

with the proviso that at least one of the following conditions is fulfilled: (a) G is a monovalent organic group that contains a silyl group of the formula:




Application No.: 10/053396

Case No.: 56313US009

wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y^1 , Y^2 and Y^3 representing a hydrolyzable group; or (b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group.


2. (Currently Amended) Fluorochemical composition according to claim 1 wherein at least one of Y^1 , Y^2 and Y^3 and/or at least one of Y^4 , Y^5 and Y^6 is a hydrolyzable group selected from the group consisting of halogen, an alkoxy group, an acyloxy group, an acyl group, and an aryloxy group.

3. (Original) Fluorochemical composition according to claim 1 wherein said monovalent organic group G corresponds to the general formula:



wherein Y^1 , Y^2 , Y^3 have the meaning as defined in claim 1 or 2 and wherein Q^1 represents an organic divalent linking group.

4. (Original) Fluorochemical composition according to claim 1 wherein M^f comprises a unit derived from a fluorinated monomer of the formula:




wherein E^1 represents a free radical polymerizable group and Q^2 represents an organic divalent linking group.

5. (Currently Amended) Fluorochemical composition according to claim 1 wherein M^g is a unit derived corresponding to the formula:


Application No.: 10/053396

Case No.: 56313US009



wherein R^1 , R^2 and R^3 each independently represents hydrogen, an alkyl group, an aryl group or halogen, Q^3 represents an organic divalent linking group, Q^4 represents an organic divalent linking group, T represents O or NR with R being hydrogen, an aryl or a C_1 - C_4 alkyl group, and Y^4 , Y^5 and Y^6 have the meaning as defined in claim 1.


6. (Original) Fluorochemical composition according to claim 1 wherein G corresponds to the formula:



wherein Q^1 and Q^5 each independently represents an organic divalent linking group, T^2 represents O or NR with R being hydrogen, an aryl or a C_1 - C_4 alkyl group, and Y^1 , Y^2 and Y^3 have the meaning as defined in claim 1.

7. (Original) Fluorochemical composition according to claim 1 wherein the composition is a homogeneous composition further comprising water and an organic or inorganic acid.

8. (Currently Amended) Fluorochemical composition according to claim 1 wherein the units derived from non-fluorinated monomers ~~are units derived from non-fluorinated monomers~~ corresponding to the general formula:



Application No.: 10/053396

Case No.: 56313US009

wherein R^h represents a hydrocarbon group, Q^6 is a divalent linking group, s is 0 or 1 and E^3 is a free radical polymerizable group.

9. (Original) Method of treating a substrate comprising applying to said substrate a composition according to claim 1.


10. (Original) Method of treating a substrate comprising applying to said substrate a composition according to claim 1 and exposing a thus obtained coated substrate to water and an organic or inorganic acid.

11. (Original) Method of treating a substrate according to claim 9 further comprising the step of exposing the coated substrate to an elevated temperature of 60°C to 300°C.

12. (Currently Amended) Method according to claim 9 wherein said substrate is selected from the group consisting of plastics, ceramics, and glass.


13. (Currently Amended) Substrate comprising a coating derivable from the coating composition of any of claim 1 wherein the substrate is selected from the group consisting of plastics, ceramics, and glass.

14. (Original) Fluorochemical oligomer corresponding to the formula:



wherein X represents the residue of an initiator or hydrogen;


M^f represents units derived from fluorinated monomers having the formula:



wherein E^1 represents a free radical polymerizable group and Q^2 represents an organic divalent linking group; M^h represents units derived from non-fluorinated monomers; M^a represents units having a silyl group represented by the formula:


Application No.: 10/053396

Case No.: 56313US009




wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group, with the proviso that at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group; G represents a monovalent organic group comprising the residue of a chain transfer agent; n represents an integer of 1 to 100; m represents an integer of 0 to 100; r represents an integer of 0 to 100; and $n+m+r$ is at least 2;

with the proviso that at least one of the following conditions is fulfilled: (a) G is a monovalent organic group that contains a silyl group of the formula:



wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y^1 , Y^2 and Y^3 representing a hydrolyzable group; or (b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group.


15. (Currently Amended) Fluorochemical oligomer having the formula:



wherein X represents the residue of an initiator or hydrogen; M^f represents units derived from fluorinated monomers; M^h represents units derived from non-fluorinated monomers; M^a represents units having the formula:


Application No.: 10/053396

Case No.: 56313US009



wherein R^1 , R^2 and R^3 each independently represents hydrogen, an alkyl group, an aryl group or halogen, Q^3 represents an organic divalent linking group, Q^4 represents an organic divalent linking group, T represents O or NR with R being hydrogen, an aryl or a C_1 - C_4 alkyl group, and wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group, with the proviso that at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group; G represents a monovalent organic group comprising the residue of a chain transfer agent; n represents an integer of 1 to 100; m represents an integer of 0 to 100; r represents an integer of 1 to 100; and $n+m+r$ is at least 2.

16. (Original) Fluorochemical oligomer according to claim 15 wherein G corresponds to the formula:



wherein Q^1 and Q^5 each independently represents an organic divalent linking group, T^2 represents O or NR with R being hydrogen, an aryl or a C_1 - C_4 alkyl group, and Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y^1 , Y^2 and Y^3 representing a hydrolyzable group.


17. (Original) Fluorochemical oligomer having the formula:




Application No.: 10/053396

Case No.: 56313US009

wherein X represents the residue of an initiator or hydrogen; M^f represents units derived from fluorinated monomers; M^h represents units derived from a non-fluorinated monomers; M^a represents units having a silyl group represented by the formula:



wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group, with the proviso that at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group; G corresponds to the formula:



wherein Q^1 and Q^5 each independently represents an organic divalent linking group, T^2 represents O or NR with R being hydrogen, an aryl or a C_1 - C_4 alkyl group, and Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y^1 , Y^2 and Y^3 representing a hydrolyzable group; n represents an integer of 1 to 100; m represents an integer of 0 to 100; r represents an integer of 0 to 100; and $n+m+r$ is at least 2.

Application No.: 10/053396

Case No.: 56313US009

Respectfully submitted,

Oct 4, 2005
Date

By: Robert H. Jordan
Robert H. Jordan, Reg. No.: 31,973
Telephone No.: 651-733-6866

Office of Intellectual Property Counsel
3M Innovative Properties Company
Facsimile No.: 651-736-3833